

10/533 921
Rec'd PTO 04 MAY 2005

#4

RECEIVED

19 DEC 2003

WIPO PCT

PI 1105138

THE UNITED STATES OF AMERICA

TO ALL TO WHOM THESE PRESENTS SHALL COME:

UNITED STATES DEPARTMENT OF COMMERCE
United States Patent and Trademark Office

December 16, 2003

THIS IS TO CERTIFY THAT ANNEXED HERETO IS A TRUE COPY FROM
THE RECORDS OF THE UNITED STATES PATENT AND TRADEMARK
OFFICE OF THOSE PAPERS OF THE BELOW IDENTIFIED PATENT
APPLICATION THAT MET THE REQUIREMENTS TO BE GRANTED A
FILING DATE.

APPLICATION NUMBER: 60/418,957

FILING DATE: October 16, 2002

RELATED PCT APPLICATION NUMBER: PCT/US03/32427



By Authority of the
COMMISSIONER OF PATENTS AND TRADEMARKS

N. Woodson
N. WOODSON
Certifying Officer

PRIORITY DOCUMENT

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)

BEST AVAILABLE COPY

10/16/02


3598 U.S. PTO

10-17-02 5:41:53 PM 10/16/02

Please type a plus sign (+) inside this box → ☒

Approved for use through 10/31/2002 OMB 0651-0032
 U.S. Patent and Trademark Office, U.S. DEPARTMENT OF COMMERCE
 Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

PROVISIONAL APPLICATION FOR PATENT COVER SHEET This is a request for filing a PROVISIONAL APPLICATION FOR PATENT under 37 CFR 1.53(c).

INVENTOR(S)					
Given Name (first and middle (if any))	Family Name or Surname	Residence (City and either State or Foreign Country)			
Priyadarshi Gautam	Desai	Bridgeville, PA USA			
Duane L.	DeBastiani	Moon, PA USA			
<input checked="" type="checkbox"/> Additional Inventors are being named on the _____ separately numbered sheets attached hereto					
TITLE OF THE INVENTION (280 characters max) RESIN-BONDED, GAS PURGED NOZZLE					
Direct all correspondence to: CORRESPONDENCE ADDRESS,					
<input checked="" type="checkbox"/> Customer Number		25105		<input checked="" type="checkbox"/> Patent Bar 	
OR		Type Customer Number here			
<input type="checkbox"/> Firm or Individual Name		VESUVIUS 25105			
Address		27 Noblestown Road			
Address					
City	Carnegie	State	PA	ZIP	15106-1632
Country	USA	Telephone	412-429-1800	Fax	412-256-7252
ENCLOSED APPLICATION PARTS (check all that apply)					
<input checked="" type="checkbox"/> Specification Number of Pages		19		<input type="checkbox"/> CD(s), Number	
<input checked="" type="checkbox"/> Drawing(s) Number of Sheets		1		<input checked="" type="checkbox"/> Other (specify)	
<input checked="" type="checkbox"/> Application Data Sheet See 37 CFR 1.76		RETURN RECEIPT POST CARD EXPRESS MAIL CERTIFICATE			
METHOD OF PAYMENT OF FILING FEES FOR THIS PROVISIONAL APPLICATION FOR PATENT (check one)					
<input type="checkbox"/> Applicant claims small entity status See 37 CFR 1.27.					
<input type="checkbox"/> A check or money order is enclosed to cover the filing fees					
<input checked="" type="checkbox"/> The Commissioner is hereby authorized to charge filing fees or credit any overpayment to Deposit Account Number.					
<input type="checkbox"/> Payment by credit card Form PTO-2038 is attached.					
				FILING FEE AMOUNT (\$)	220281
					\$160
The invention was made by an agency of the United States Government or under a contract with an agency of the United States Government.					
<input checked="" type="checkbox"/> No					
<input type="checkbox"/> Yes, the name of the U.S. Government agency and the Government contract number are					

Respectfully submitted,

SIGNATURE

Date 16/Oct/02

TYPED or PRINTED NAME James R. Williams

REGISTRATION NO.
(if appropriate)
Docket Number

43,268

TELEPHONE 412-429-1800 x252

1415

USE ONLY FOR FILING A PROVISIONAL APPLICATION FOR PATENT

This collection of information is required by 37 CFR 1.51. The information is used by the public to file (and by the PTO to process) a provisional application. Confidentiality is governed by 35 U.S.C. 122 and 37 CFR 1.14. This collection is estimated to take 8 hours to complete, including gathering, preparing, and submitting the complete provisional application to the PTO. Time will vary depending upon the individual case. Any comments on the amount of time you require to complete this form and/or suggestions for reducing this burden, should be sent to the Chief Information Officer, U.S. Patent and Trademark Office, U.S. Department of Commerce, Washington, D.C. 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Box Provisional Application, Assistant Commissioner for Patents, Washington, D.C. 20231.

5010957-101607

PROVISIONAL APPLICATION COVER SHEET
Additional Page

PTO/SB/16 (8-00)
Approved for use through 10/31/2002 OMB 0651-0032
U S Patent and Trademark Office, U S DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number

Docket Number		1415	Type a plus sign (+) inside this box →	+
INVENTOR(S)/APPLICANT(S)				
Given Name (first and middle (if any))	Family or Surname	Residence (City and either State or Foreign Country)		
Dominique	Janssen	McKees Rocks, PA, USA		

Number 2 of 2

WARNING: Information on this form may become public. Credit card information should not be included on this form. Provide credit card information and authorization on PTO-2038.

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

In re Application of) DESAI et al.
 Title) RESIN BONDED,
) GAS PURGED NOZZLE
 Attorney's Docket) 1415 US

To: Assistant Commissioner for Patents
 Box PROVISIONAL PATENT APPLICATION
 Washington, D.C. 20231


Express Mail Certificate

Date of Deposit: October 16, 2002

To: Assistant Commissioner for Patents

I hereby certify that this correspondence is being deposited with the United States Postal Service as "Express Mail Post Office to Addressee" under 37 C.F.R. 1.10 on the date indicated above and was addressed to the Assistant Commissioner for Patents, Box PROVISIONAL PATENT APPLICATION, Washington, D.C. 20231.

Express Mail number EU 084867588 US



Signature of person mailing correspondence

Thomas C. Dunford

Name of person mailing correspondence

Application Data Sheet

Application Information

Application Type:	Provisional
Subject Matter:	Utility
Suggested Classification:	
Suggested Group Art Unit:	
CD-ROM or CD-R?	None
Title:	RESIN-BONDED, GAS PURGED NOZZLE
Request for Early Publication?:	No
Request for Non-Publication?:	No
Suggested Drawing Figure:	1
Total Drawing Sheets:	1
Small Entity:	No
Petition Included?:	No
Secrecy Order in Parent Appl.?:	No

Applicant Information

Applicant Authority Type:	Inventor
Primary Citizenship Country:	India
Given Name:	Priyadarshi Gautam
Family Name:	Dasai
City of Residence:	Bridgeville
State of Residence:	Pennsylvania
Country of Residence:	US
Street of mailing address:	7081 Highland Creek Road
State of mailing address:	Pennsylvania
Zip Code of mailing address:	15017

Applicant Information

Applicant Authority Type: Inventor
 Primary Citizenship Country: US
 Given Name: Duane L.
 Family Name: DeBastiani
 City of Residence: Moon
 State of Residence: Pennsylvania
 Country of Residence: US
 Street of mailing address: 603 Parliament Drive
 State of mailing address: Pennsylvania
 Zip Code of mailing address: 15108

Applicant Authority Type: Inventor
 Primary Citizenship Country: Canada
 Given Name: Dominique
 Family Name: Janssen
 City of Residence: McKees Rocks
 State of Residence: Pennsylvania
 Country of Residence: US
 Street of mailing address: 12 Wellington Court
 State of mailing address: Pennsylvania
 Zip Code of mailing address: 15136

Correspondence Information

Correspondence Customer Number: 25105

Representative Information

Representative Customer Number: 25105

Domestic Priority Information

Application:	Continuity Type:	Parent Application:	Parent Filing Date:
None			

Foreign Priority Information

Country:	Application Number:	Filing Date:	Priority Claimed:
None			

Assignee Information

Assignee Name: Vesuvius Crucible Corporation
Assignee Address: 103 Foulk Road
Assignee City: Wilmington
Assignee State: DE
Assignee Zip Code: 19803

RESIN-BONDED, GAS PURGED NOZZLE

Inventors:

5 Priyadarshi Gautam Desai
7081 Highland Creek Road
Bridgeville, PA 15017
County: Allegheny
Citizenship: India

Duane L. DeBastiani
603 Parliament Drive
Moon, PA 15108
Allegheny
USA

Dominique Janssen
12 Wellington Court
McKees Rocks, PA 15136
Allegheny
Canada

10

The present invention is being submitted as a provisional application under 37
CFR 1.53(c).

FIELD OF THE INVENTION

15 This invention relates to a refractory nozzle for use in the casting of molten steel,
and particularly to a nozzle that uses inert gas for reducing unwanted accumulation of
alumina deposits at the steel/nozzle interface.

BACKGROUND OF THE INVENTION

20 Refractory articles for controlling a flow of molten metal, such as steel, are
known in the prior art. Such articles include nozzles, slide gate plates, stopper rods and
shrouds, and are often used in combination to modulate a flow of liquid steel during the
casting of molten metal. In the 1970's, aluminum-killed steels became one of the most
common products of the steel making industry due to its desirable metallurgical
properties.

25 Unfortunately, during casting, metal oxides, such as alumina, deposit and
accumulate on surfaces where molten steel contacts the refractory articles. Contacting
surfaces include, for example, the bore and top surface of a nozzle. Oxide deposits in the
bore can ultimately cause the complete blockage of the nozzle. Alternatively, deposits at

the top surface can prevent shut-off of the molten steel stream because a stopper rod can no longer sealingly engage the top surface of the nozzle.

Research has shown that alumina deposits form when oxygen reacts with constituents in the nozzle and the molten steel. Shielding the molten steel from oxygen effectively reduces unwanted deposits. Shielding may be accomplished by injecting an overpressure of inert gas, such as argon, into the refractories surrounding the molten steel. Injection reduces the partial pressure of oxygen available to cause clogging.

Nozzle assemblies that permit inert gas injection frequently include a refractory article and a metal can. The refractory article is usually secured in the metal can with a refractory mortar. The article may include a gas delivery system comprising a plurality of holes opening onto a contacting surface, or a porous, gas-conducting refractory element adjacent to a contacting surface. The latter is typically surrounded by or imbedded in a second refractory component. The nozzle assembly may also include a gas delivery system comprising channels, grooves or devices, within or outside the nozzle that direct inert gas to the holes or porous elements. Examples of such nozzles include U.S. Pat. Nos. 4,360,190; 5,100,035, 5,137,189, and 5,723,055.

The metal can acts as an impervious barrier, thereby reduces the likelihood that oxygen will diffuse into the refractory article and injected inert gas will escape from the article. The metal can, therefore, reduces the amount of gas needed to maintain a low partial pressure of oxygen. Unfortunately, gas can still leak from the nozzle assembly, and oxygen can still find its way into the nozzle assembly. The mortar interface between the metal can and the refractory nozzle is highly permeable to gas diffusion. Differences in thermal expansion often create a gap between the metal can and the refractory. Also,

the metal can substantially degrade during casting. High temperatures combined with mechanical stress can induce significant creep and plastic behavior in the metal can. The metal can perforate, thereby becoming incapable of containing the inert gas within the refractory article or preventing oxygen from aspirating into the molten metal.

5 Besides diffusion of oxygen around or through the metal can, oxygen may also be present as a contaminate in the inert gas. Impure inert gas and leaks in the gas feed lines can also allow significant quantities of oxygen to pass to the porous element. Oxygen readily passes through prior art porous elements and can react with the molten steel to form deposits. Prior art elements typically consist of carbon-bonded materials or oxide-
10 bonded material, and do not remove oxygen from the incoming stream of gas.

 A need exists for a refractory nozzle that better shields the molten steel from oxygen. Prior art nozzles still permit the diffusion of oxygen through the article and into the molten steel. Metal cans do not completely prevent oxygen diffusion to the molten steel. Oxygen can still penetrate along the interface between the article and the metal can
15 and is able to pass through the metal can at casting temperatures. Furthermore, "canning" significantly adds to the expense of the product. Preferably, the nozzle would include a gas impermeable barrier with a thermal expansion coefficient similar to the porous element. Advantageously, shielding would include both mechanical and chemical means. More preferably, the porous element would scavenge or scrub whatever oxygen was
20 present in the inert gas or was able to penetrate through the barrier.

SUMMARY OF THE INVENTION

 The present invention describes a porous, resin-bonded composition and a refractory nozzle comprising the composition. The porous resin-bonded composition

may be used in the casting of molten steel in order to reduce the accumulation of deposits on surfaces exposed to a stream of molten steel. Surfaces include the bore or top sealing surface of the resin-bonded nozzle.

In a broad aspect, the permeable material includes a porous, resin-bonded composition that is permeable to inert gas. Permeability may be controlled, for example, by adjusting particle size, forming pressure, level of fugitive additives, or drilling holes in the material. The composition includes refractory aggregate, binder and oxygen getters. The latter includes reactive metals and certain boron compounds. Refractory aggregate includes any suitable refractory material, such as alumina, magnesia, silica, zirconia, calcia, and mixtures and compounds thereof. The cured composition retains a permeability of at least 50 cD.

One embodiment includes a permeable material made from a particulate refractory mixture comprising at least about 60 wt.% aggregate having a particle size of +80 mesh or higher, less than 20 wt.% aggregate having a particle size of +325 to -80 mesh, and less than 20 wt.% aggregate having a particle size less than -325 mesh.

The permeable material may be included as a porous element in an article for protecting molten steel from oxygen. The porous element is positioned to permit the introduction of inert gas into or around the molten steel stream. Advantageously, the porous element comprises oxygen getters that scrub oxygen from the inert gas so that residual oxygen cannot induce the accumulation of deposits.

An impermeable material substantially surrounds the porous element, thereby containing the inert gas within the article and directing the inert gas into and through the porous element toward the molten steel. Conveniently, one can control the porosity of

the permeable composition and the diffusion of inert gas into the molten steel.

Alternatively or in conjunction with porosity, a gas delivery system, such as channels, grooves or devices, may facilitate the delivery and diffusion of inert gas through the permeable material.

5 In one embodiment, the permeable material is co-pressed with a resin-bonded gas impermeable composition to form a refractory article. Use of the impermeable composition permits the elimination of a metal can, thereby saving on manufacturing costs and eliminating the permeable interface between the can and the refractory. Unlike a metal can, the impermeable composition has a thermal expansion coefficient similar to
10 the permeable composition, and does not deteriorate at casting temperatures.

The method of the present invention includes copressing an impermeable composition around a permeable composition. Heating the compositions above about 150°C, and preferably above about 200°C, for a sufficient time to create a resin bond and, unlike carbon- and oxide-bonded compositions, avoiding premature reaction of the
15 oxygen getters.

BREIF DESCRIPTION OF THE DRAWINGS

Figure 1 shows a cross-section of a refractory nozzle of the prior art.

Figure 2 shows a cross-section of a refractory nozzle of the present invention.

DETAILED DESCRIPTION OF THE INVENTION

20 The present invention describes a permeable, resin-bonded composition, and a canless, resin-bonded refractory nozzle comprising the composition that may be used to inject gas into a flow of molten metal. Resin-bonded means pressed, particulate compositions that cure at temperatures less than 800°C, and usually at temperatures less

Advantageously, low curing temperatures permit the addition and retention of various beneficial compounds. For example, reactive metals, such as aluminum and magnesium, will oxidize or form carbides at elevated temperatures, but will remain in their elemental state during resin-bonded curing. Unfortunately, resin-bonded compositions are typically impermeable to gases and are not amendable to use as a porous element for a gas-injection nozzle. Permeability is measured by according to ASTM Standard C-577, and involves forming a 2 inch cube of the material to be tested, applying a backpressure of 3-6 psi, and measuring the flow rate through the cube.

After exposure to a temperature of 1000°C, which corresponds to preheating of a refractory article in the continuous casting of steel, resin-bonded compositions will often have a permeability of less than about 15 cD. More commonly, permeability is less than 5 cD. A porous element should have a permeability of at least about 50 cD.

The present resin-bonded, permeable composition comprises refractory aggregate, binder and oxygen getters. Refractory aggregate includes any suitable refractory material, such as alumina, zirconia, calcia, and mixtures and compounds thereof. Preferably, compounds that produce volatile oxides at elevated temperatures, such as silica and magnesia, should be limited.

The permeable composition comprises a resin-bonded composition having a permeability of at least about 50 cD, a porosity of at least about 15%, and a median pore

size of 5 microns. Preferably, permeability is above 100 cD; porosity is greater than 20%; and median pore size is greater than 10 microns. In contrast, a standard resin-bonded composition comprises a permeability of less than 25 cD, a porosity of 9-14%, and a median pore size of 2-4 microns. By comparison, a standard, tar-impregnated carbon-bonded composition comprises a permeability of less than 10 cD, a porosity of less than 20%, and a median pore size of about 1 micron.

Permeability may be altered by various methods, including pressing, particle size distribution, fugitive additives, drilling, and chemical compositions, either individually or in combination. Theoretically, reducing the pressure of pressing to only 1000-3000 would increase permeability, but physical properties, particularly erosion- and corrosion-resistance can significantly decrease. Fugitive additives include materials that volatilize or melt below casting temperatures, and include waxes or other organic materials. Lasers may also be used to drill small holes in the material, thereby creating gas channels in the material. Various chemicals can induce gas formation, thereby generating pores in the material. Other chemicals, such as fluxes, can decrease porosity.

Preferably, permeability is controlled by the particle size distribution of the refractory aggregate. The distribution comprises a majority of a large particle size aggregate and a small particle size aggregate that does not completely fill interstices between the large aggregate. The smaller particle size aggregate should be at least about one-third, and preferably one-half, the size of interstices of the large aggregate. A third aggregate having an even smaller particle size may be added to fine-tune porosity, facilitate processing, or improve strength of the cured article. In one embodiment, a suitable particle size distribution includes at least about 60 wt.% aggregate having a

particle size of +80 mesh or higher, less than 20 wt.% aggregate having a particle size of +325 to -80 mesh, and less than 20 wt.% aggregate having a particle size less than -325 mesh.

The curable resin binder should be present in an amount to achieve adequate green strength after pressing and curing. Pressing will usually be at least about 3000 psi to achieve good erosion- and corrosion-resistance. Curing for a resin-bonded composition typically occurs at or below around 300°C. For additional strength, the composition may be heat treated at a temperature below about 800°C and most preferably below about 500°C. One must be exercise caution when heat treating because permeability may change at elevated temperatures. The amount of binder will vary depending on, for example, the type of binder used and the desired green strength. A sufficient amount of binder will typically be from 1-10 wt.%. Typically, the binder is organic and usually the binder is a carbon-based resin, such as, phenolic resins, carbonaceous binders derived from pitch or resin, starch, or ligno-sulfonates.

The gas-impermeable composition also comprises an oxygen getter. An oxygen getter reacts with oxygen that diffuses into or forms within the gas-impermeable composition, thereby making the oxygen unavailable to the molten steel. Common oxygen getters include, for example, boron compounds, carbides, nitrides, and reactive metal powders such as aluminum, magnesium, silicon and mixtures and alloys thereof. Boron compounds are particularly effective oxygen getters, and include elemental boron, boron nitride, boron carbide, and mixtures thereof. Because boron compounds can act as a flux, thereby reducing porosity, their use should be carefully limited.

The needed quantity of oxygen getter depends on the particular use to which the

refractory article will be placed. A minimum of 0.25 wt.% is believed necessary to show demonstrable improvement in oxidation-resistance. Alternatively, more than 15 wt.% is costly, typically unnecessary, and may even be hazardous such as when using reactive metal powders. Additionally, oxygen getters may decrease thermal shock-resistance and
5 erosion-resistance of the article.

A preferred oxygen getter comprises a reactive metal, including aluminum, magnesium, silicon, titanium, and mixtures and alloys thereof. Conveniently, reactive metals are added as powders, flakes and the like. The reactive metal should be present in sufficient quantity so that, during casting of molten steel, the reactive metal scavenges
10 any oxygen that may diffuse into or emanate from the refractory article. Various factors affect the amount of reactive metal that will be sufficient to scavenge oxygen. For example, the inclusion of oxygen-releasing compounds, such as silica, require higher levels of reactive metal in order to scavenge the released oxygen. Limitations on the amount of reactive metal include cost and hazardousness. Reactive metals are generally
15 more expensive than refractory aggregates and, especially as powders, reactive metals can be explosive during processing. A typical amount of reactive metal is from 5-12 wt.%.

Graphite may be added to the permeable, resin-bonded composition in order to improve thermal-shock resistance. Preferably, the level of graphite will not exceed about
20 10 wt.%. Graphite has been correlated with alumina deposition, so the amount of graphite should be kept as low as needed.

The nozzle of the present invention includes a porous, resin-bonded element, surrounded by an impermeable element, such as a metal can or impermeable refractory

composition. Nozzle means any refractory article used to conduct a flow of molten metal, including ladle and tundish nozzles such as well nozzles, subentry nozzles, subentry shrouds, and collector nozzles.

Figure 1 shows a nozzle 1 of the prior art. A porous element 2 forms at least a portion of the inner surface 3 of the nozzle 1, and is adapted to deliver inert gas to the bore 4 of the nozzle 1. The bore 4 is adapted to transfer the steel from the nozzle inlet 5 to the nozzle outlet 6. The porous element 2 is at least partially surrounded by a nozzle body 7 comprising a second refractory material. The refractory elements are mortared at least in part within a metal can 8. During casting, a conduit 9 delivers inert gas to the nozzle 1. The inert gas may also pass through a combination of channels, grooves or devices within or surrounding the nozzle 1.

The porous element 2 typically comprises an oxide-bonded or phosphate-bonded material having a relatively open pore structure and a permeability of at least about 50 cD, and more frequently greater than 150 cD. A typical porous element includes an oxide-bonded magnesia, an alumina-chrome, or high alumina composition. The second refractory material is usually a carbon-bonded or castable refractory. Castable refractory includes those particulate materials to which water is added, and which subsequently harden. Examples include refractories comprising a hydratable compound, such as calcia, that react with water to form a hard product. The metal can 8 is intended to be a gas impermeable barrier, which prevents gas leakage or oxygen ingress.

Whether carbon-bonded or castable, the second material, while not porous enough to comprise the porous element, is porous enough to permit leakage of inert gas and ingress of oxygen. Numerous other opportunities exist for oxygen to contact the molten

steel. The mortar joint 10 between the nozzle body 7 and the metal can 8 is often porous and readily permits oxygen diffusion. Differences in thermal expansion between the nozzle body 7, the metal can 8, or the conduit may also produce cracking. Oxygen can flow along these cracks to the molten steel. Oxygen may also contaminate the inert gas feed, whether as a trace impurity in the gas itself or by leakage in the delivery system.

As shown in Figure 2, one embodiment of the present invention is a nozzle 1 including a porous element 2 comprising the porous, resin-bonded composition. The porous element 2 is surrounded at least in part by a nozzle body 7 comprising a substantially impermeable material. The impermeable material may comprise a metal can but, as shown in Fig. 2, the impermeable material may comprise a second resin-bonded composition. The second resin-bonded composition is substantially impermeable to gas, and substitutes for the metal can of the prior art. Advantageously, a mortar joint is unnecessary, and the impermeable refractory does not deteriorate at casting temperatures.

In an alternative embodiment, the nozzle body may substantially comprise a permeable material and even a porous, resin-bonded composition provided an impermeable material substantially forms the outer surface of the nozzle body. Conveniently, the impermeable material comprises a metal can and the remainder of the nozzle consists essentially of a refractory ceramic material. The refractory ceramic material may comprise a plurality of ceramic components, or may simply consist of the porous element. Advantageously, the latter embodiment is easily manufactured using a single pressing step, a single curing step, and a single canning step.

The impermeable material of the nozzle should have a permeability of less than about 15 cD, and preferably less than 5 cD. One skilled in the art is aware of various

impermeable ceramic or metallic materials, and several methods to produce an impermeable ceramic material using a variety of chemical and mechanical means. For examples, fluxes, glazes, particle size distribution, bonding system, composition of the refractory, and processing conditions can individually and in combination affect permeability. Fluxes introduce low temperature phases and facilitate vitrification. Glazes produce an impervious coating on the surface of the refractory. Particle size distribution in a refractory aggregate can substantially affect porosity, and ultimately permeability, in a finished product. Processing conditions, such as firing temperature and pressing, have profound effects on permeability. Chemical compositions of the refractory and bonding system also substantially affect permeability.

The impermeable composition preferably comprises a resin-bonded composition. The impermeable composition includes at least one refractory aggregate, a curable resin binder and a reactive metal. Refractory aggregate includes any refractory material suitable for steel casting, including but not limited to alumina, magnesia, calcia, zirconia, silica, compounds and mixtures thereof. A typical impermeable composition comprises 50-90 wt.% refractory aggregate, 1-10 wt.% binder, and 0.5-15 wt.% reactive metal. More preferably, the impermeable composition comprises 65-80 wt.% fused alumina, 2-30 wt.% calcined alumina, 1-10 wt.% binder, 0.5-10 wt.% aluminum metal, up to 15 wt.% zirconia, and less than 3 wt.% silica. Graphite may be added for processing or thermal-shock resistance, and is conveniently added at levels of 0.5-10 wt.%.

Gas delivery systems can increase gas transport in the refractory nozzle. Such systems comprise channels, grooves or devices within or on a surface of the refractory article. The device can be perforated to permit uniform distribution of gas along its

length. Channels are frequently produced by burning out wax or other low melting point material that had been pressed or cast into the refractory article.

The method of the invention includes forming the permeable composition such as, for example, by pressing or extruding, and curing the permeable composition to form the porous element. Curing occurs at temperatures below about 800°C, preferably below about 500°C, and most preferably at or below 300°C. Low cure temperature preserves the oxygen getters in the resin-bonded compositions. The impermeable composition is then placed substantially all around the porous element to form the finished refractory nozzle. Multiple firing or canning steps are avoided. In one embodiment, the permeable composition is copressed with the impermeable composition to form a pressed piece, which is cured to form the finished nozzle. Copressing will most often occur at pressures over 3000 psi to ensure adequate mechanical strength, including erosion- and corrosion-resistance. In this embodiment and unlike prior art, a metal can and high temperature firing are unnecessary.

Example 1

As shown in Table 1, the permeability of a permeable, resin-bonded composition (A) was compared with permeabilities of three, prior art compositions (B-D). Composition A comprised a permeable resin-bonded material based on an alumina aggregate. Composition B was a standard, non-permeable resin-bonded material. Composition C was a standard, permeable oxide-bonded magnesia. Composition D was a standard, fired carbon-bonded refractory. The resin-bonded compositions were cured at 200°C. The oxide-bonded material was fired at greater than 1000°C for more than four hours. The carbon-bonded composition was fired at greater than 800°C for more than

four hours in a reducing atmosphere. Permeability was performed according to ASTM Standard C-577. The permeability of the permeable resin-bonded material greatly surpassed the standard resin-bonded and carbon-bonded materials, and compared favorably with the oxide-bonded magnesia.

	A	B	C	D
	Permeable Resin-Bond	Standard Resin-Bond	Oxide-Bond	Carbon-Bond
Permeability in cD, after 1000°C	65-250	1-20	65-250	1-15

5

Example 2

Table 2 shows the oxygen scrubbing capacity of various refractory compositions. Scrubbing capacity is measured by heating samples to 1200°C in argon, exposing the samples to air at 1200°C, and weighing the samples. An increase in weight indicates the absorption of oxygen by the sample, which typically means the reaction of oxygen with a constituent in the sample to produce an oxide. Samples A-C comprise (A) a permeable resin-bonded material of the present invention, (B) an impermeable resin-bonded material, and (C) a fired, oxide-bonded magnesia composition. Sample A, the permeable resin-bonded material, absorbs substantially more oxygen at all times and continues to absorb oxygen faster than Sample B, even after three hours. Sample C, the fired refractory without oxygen getters, absorbed no oxygen.

15

	Weight Gain, %		
Time, hrs	A	B	C

1	1.9	0.9	0
2	2.4	1.1	0
3	2.7	1.2	0

Obviously, numerous modifications and variations of the present invention are possible. It is, therefore, to be understood that within the scope of the following claims, the invention may be practiced otherwise than as specifically described. While this
5 invention has been described with respect to certain preferred embodiments, different variations, modifications, and additions to the invention will become evident to persons of ordinary skill in the art. All such modifications, variations, and additions are intended to be encompassed within the scope of this patent, which is limited only by the claims appended hereto.

What is claimed:

1. A permeable, resin-bonded material having a permeability of at least about 50 cD
and made from a composition comprising:
 - a) at least 80 wt.% refractory aggregate comprising a least about 60 wt.%
5 aggregate having a particle size of +80 mesh or higher, less than 20 wt.%
aggregate having a particle size of -325 to +80 mesh, and less than 20 wt.%
aggregate having a particle size less than -325 mesh;
 - b) 0.5-15 wt.% of at least one oxygen getter; and
 - c) a sufficient amount of binder.
- 10 2. The permeable, resin-bonded material of claim 1, wherein the refractory aggregate
comprises at least one oxide selected from the group consisting of alumina,
magnesia, silica, zirconia, calcia, and mixtures and compounds thereof
3. The permeable, resin-bonded material of claim 1, wherein the oxygen getter
comprises at least one compound selected from the group consisting of boron
15 compounds, carbides, nitrides, and reactive metals.
4. The permeable, resin-bonded material of claim 3, wherein the reactive metal is
selected from the group consisting of aluminum, magnesium, silicon, titanium, and
mixtures and alloys thereof.
5. The permeable, resin-bonded material of claim 1, wherein the binder is selected
20 from the group consisting of phenolic resins, carbonaceous binders, starch, and
ligno-sulfonates.
6. A refractory nozzle for use in the casting of molten metal having an inlet, an outlet,
an outer surface, an inner surface defining a bore fluidly connecting the inlet and

the outlet, and a top surface surrounding the inlet, the nozzle adapted to receive a flow of inert gas and comprising:

- a) a permeable, resin-bonded refractory composition lining at least a portion of the inner surface; and
 - 5 b) an impermeable material surrounding at least a portion of the permeable composition, wherein the impermeable composition substantially prevents diffusion of gases through the outer surface.
7. The refractory nozzle of claim 6, wherein the permeable composition is made from a plurality of refractory aggregates of different sizes, whereby packing of the
- 10 different sizes leaves pores through which gas may diffuse.
8. The refractory nozzle of claim 7, wherein the permeable composition is made from composition comprising:
- a) at least 80 wt.% refractory aggregate comprising a least about 60 wt.% aggregate having a particle size of +80 mesh or higher, less than 20 wt.%
 - 15 aggregate having a particle size of -325 to +80 mesh, and less than 20 wt.% aggregate having a particle size less than -325 mesh;
 - b) 0.5-15 wt.% of at least one oxygen getter; and
 - c) a sufficient amount of binder.
9. The refractory nozzle of claim 6, wherein the permeable composition is made from
- 20 a resin-bonded composition comprising fugitive additives, whereby heating the composition releases the additives and produces a porous resin-bonded material.
10. The refractory nozzle of claim 6, wherein the impermeable material is selected from the group consisting of metal and an impermeable resin-bonded composition.

11. The refractory nozzle of claim 10, wherein the impermeable composition is made from a composition comprising 50-90 wt.% refractory aggregate, 1-10 wt.% binder, and 0.5-15 wt.% reactive metal.
12. The refractory article of claim 11, wherein the impermeable composition comprises
5 65-80 wt.% fused alumina, 2-30 wt.% calcined alumina, 1-10 wt.% binder, 0.5-10 wt.% aluminum metal, up to 15 wt.% zirconia, and less than 3 wt.% silica.
13. The refractory nozzle of claim 6, wherein the nozzle includes an inert gas delivery system.
14. The refractory nozzle of claim 13, wherein the gas delivery system is selected from
10 the group consisting of channels, grooves and devices.
15. A method of manufacturing a gas-injection nozzle comprising:
 - a) placing a first composition around a mandrel in a mold;
 - b) placing a second composition at least partially around the first composition;
 - c) pressing the first and second compositions together at a pressure of at least
15 about 3000 psi to form a green piece;
 - d) curing the green piece at a temperature less than 800°C to form the nozzle.

GAS PURGED NOZZLE

ABSTRACT OF THE DISCLOSURE

5

A permeable, resin-bonded composition is described, which finds utility as a porous element in a gas-injection nozzle. The permeable composition is notably useful in a canless, resin-bonded, gas-injection nozzle, wherein an impermeable, resin-bonded composition replaces the metal can. Advantageously, the resin-bonded compositions include an oxygen getter for scrubbing oxygen before the oxygen can reach the molten steel. A method of manufacturing the nozzle is described and includes copressing a standard, resin-bonded composition around the permeable, resin-bonded composition. The pressed piece may be cured at temperatures below about 800°C.

FIG. 1





FIG. 2



**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☒ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.